

Classic Range: GroE, OPzS-LA, OCSM-LA, OGi-LA, Energy Bloc Operating Instructions for stationary lead acid batteries

Nominal data

- Nominal voltage U_N : 2.0 V x number of cells
- Nominal capacity $C_N = C_{10}$: 10h discharge (see type plate on cells and technical data in these instructions)
- Nominal discharge current $I_N = I_{10}$: $C_N / 10h$
- Final discharge voltage U_f : see technical data in these instructions
- Nominal temperature t_N : 20° C

Assembly by: _____ EXIDE Technologies order no.: _____ date: _____

Commissioned by: _____ date: _____

Safety signs attached by: _____ date: _____



- Observe these Instructions and keep them located near the battery for future reference!
- Work on the battery should only be carried out by qualified personnel.



- Do not smoke!
- Do not use any naked flame or other sources of ignition.
Risk of explosion and fire!



- While working on batteries wear protective goggles and clothing!
- Observe the accident prevention rules as well as EN 50272-2, EN 50110-1!



- Any acid splashes on the skin or in the eyes must be rinsed with plenty of clean water immediately. Then seek medical assistance.
Spillages on clothing should be rinsed out with water!



- Explosion and fire hazard, avoid short circuits.



- Electrolyte is strongly corrosive!



- Blocs/cells are very heavy! Make sure they are installed securely! Only use suitable means of transport!
- Bloc/cell containers are sensitive to mechanical damage.
- Handle with care!



- Caution! Dangerous voltage.
- Metal parts of the battery are always alive, therefore do not place items or tools on the battery!

Non-compliance with operating instructions and installations or repairs made with other than original accessories and spare parts or with accessories and spare parts not recommended by the battery manufacturer or repairs made without authorization and use of additives for the electrolytes (alleged enhancing agents) render the warranty void.



Spent batteries have to be collected and recycled separately from normal household wastes (EWC 160601). The handling of spent batteries is described in the EU Battery Directive (91/157/EEC) and their national transitions (UK: HS Regulation 1994 No. 232, Ireland: Statutory Instrument No. 73/2000). Contact your supplier to agree upon the recollection and recycling of your spent batteries or contact a local and authorized Waste Management Company.

1. Start Up

Check all cells/blocs for mechanical damage, correct polarity and firmly seated connectors. The following torques apply to the cell types:

GroE, OCSM, OGi-Bloc	OPzS, Energy Bloc	OGi-Cells	
		≤ 250Ah	≥ 260Ah
25Nm ±1	20Nm±1	8Nm ±1	25Nm ±1

Put covers on the terminals if necessary. Check the electrolyte level in all cells and if necessary top up to maximum level with purified water as acc. to DIN 43530 Part 4. Connect the battery

with the correct polarity to the charger (pos. pole to pos. terminal). The charger must not be switched on during this process, and the load must not be connected. Switch on charger and start charging following item 2.2.

2. Operation

For the installation and operation of stationary batteries EN 50 272-2 is mandatory.

The battery must be installed in a way which prevents ambience-dependent temperature differences of >10 K arising. The spacing between the cells or blocs should be 10 mm and at least 5 mm in rack mounting.

2.1 Discharge

Discharge must not be continued below the voltage recommended for the discharge time. Deeper discharges must not be carried out unless specifically agreed with the manufacturer. Recharge immediately following complete or partial discharge.

2.2 Charging

All charging characteristics with their specific data, described in
DIN 41773 (IU-characteristic)
DIN 41774 (W-characteristic)
DIN 41776 (I-characteristic)
may be used. According to the charging equipment, specification and characteristics alternating currents flow through the battery superimposing onto the direct current during charge operation.

Alternating currents and the reaction of the loads may lead to an additional temperature increase of the battery, and strain the electrodes with possible damage (see point 2.5), which can shorten the battery life. Depending on the installation, charging (acc. to DIN EN 50272-2) may be carried out in following operations:

a) Standby Parallel Operation

Here the load, battery and battery charger are continuously in parallel. Thereby, the charge voltage is the operation voltage and at the same time the battery installation voltage.

With the standby parallel operation, the battery charger is capable, at any time, of supplying the maximum load current and the battery charging current. The battery only supplies current when the battery charger fails. The charge voltage measured at the end terminals of the battery should be set at see table. To reduce the charging time, a boost-charging stage can be applied in which the charge voltage of (2.33 - 2.40) Vpc ±1% x number of cells can be adjusted (standby parallel operation with boost recharging stage). Automatic changeover to charging voltage acc. to table.

b) Buffer Operation

With buffer operation, the battery charger is not able to supply the maximum load current at all times. The load current intermittently exceeds the nominal current of the battery charger. During this period the battery supplies power. This results in the battery not being fully charged at all times. Therefore, depending on the load the charge voltage must be set at (2.27 - 2.30) Vpc ±1% x number of cells. This has to be carried out in accordance with the manufacturers instructions.

Recommended charge voltage:

Range	Charge voltage
GroE, OPzS-LA, OGi-LA, Energy Bloc	2.23V ±1% x number of cells
OCSM-LA	2.25V ±1% x number of cells

c) Switch mode operation

When charging, the battery is separated from the load. Towards the end of the charging process the charge voltage of the battery is 2.6 V - 2.75 V times the number of cells. The charging process must be monitored (see points 2.4, 2.5 and 2.6). On reaching a fully charged state, the charging process must be stopped or switched to float charge as in point 2.3.

d) Battery Operation (charge-/discharge operation)

The load is supplied by the battery only, whereby the charge voltage of the battery towards the end of the charging process can be 2.6 V - 2.75 V times the number of cells. The charging process must be monitored (see points 2.4, 2.5 and 2.6). On reaching a fully charged state, the charging process must be switched off. The battery can be switched to the load as required.

2.3 Maintaining full charge (float charging)

The devices used must comply with the stipulations under DIN 41773. They are to be set so that the average cell voltage is see table 2.2 and the electrolyte density should not decrease over a lengthy period.

2.4 Equalizing charge

Because it is possible to exceed the permitted load voltages, appropriate measures must be taken, e.g. switch off the load.

Equalizing charges are required after deep discharges and/or inadequate charges. They can be carried out as follows:

- at constant voltage of max. 2.4 Vpc up to 72 hours
- with I- or W-characteristic as in point 2.6.

The electrolyte temperature must never exceed 55° C. If it does, stop charging or revert to float charge to allow the temperature to drop.

The end of the equalizing charge is reached when the electrolyte density and the cell voltages no longer increase over a period of 2 hours.

2.5 Alternating currents

When recharging up to 2.4 Vpc under operation modes 2.2 the value of the alternating current is occasionally permitted to reach 20 A (RMS) per 100 Ah nominal capacity.

When recharging over 2.4 Vpc the RMS value may not exceed 10 A per 100 Ah nominal capacity. In a fully charged state during float charge or standby parallel operation the actual value of the alternating current must not exceed 5 A (RMS) per 100 Ah nominal capacity.

2.6 Charging currents

The charging currents are not limited during standby parallel operation or buffer operation. Exceeding this voltage increases water decomposition. The charging currents per 100 Ah nominal capacity shown in the following table must not be exceeded.

Charging procedure	Cell series		Cell voltage
	GroE	OGi, OPzS, OCSM, Energy Bloc	
I-characteristic	6.5A	5.0A	2.60V-2.75V
W-characteristic	9.0A	7.0A	at 2.40V at 2.65V
	4.5A	3.5A	

2.7 Temperature

The recommended operating temperature range for lead acid batteries is 10° C to 30° C. All technical data apply to the nominal temperature 20° C.

The ideal operating temperature is 20° C ± 5 K. Higher temperatures will seriously reduce service life. Lower temperatures reduce the available capacity. The absolute maximum temperature is 55° C.

2.8 Temperature-related charge voltage

A temperature related adjustment of the charge voltage within the operating temperature of 10° C to 30° C is not necessary. If the operating temperature is constantly outside this range, the charge voltage has to be adjusted.

The temperature correction factor is -0.004 Vpc per K. If the temperature is constantly in excess of 40° C, the factor is -0.003 Vpc per K.

2.9 Electrolyte

The electrolyte is diluted sulphuric acid. The nominal electrolyte density (± 0.01 kg/l) is based on 20° C when fully charged and with the maximum electrolyte level. Higher temperatures reduce electrolyte density, lower temperatures increase electrolyte density. The appropriate correction factor is -0.0007 kg/l per K.

Example: electrolyte density of 1.23 kg/l at 35° C corresponds to a density of 1.24 kg/l at 20° C or an electrolyte density of 1.25 kg/l at 5° C corresponds to a density of 1.24 kg/l at 20° C.

3. Battery maintenance and control

The electrolyte level must be checked regularly. If it drops to the lower electrolyte level mark, purified water must be added in accordance with DIN 43530 Part 4 (maximum conductivity 30 µS/cm). Keep the battery clean and dry to avoid leakage currents. Plastic parts of the battery, especially containers, must be cleaned with pure water without additives.

At least every 6 months measure and record:

- Battery voltage
- Voltage of some cells/bloc batteries
- Electrolyte temperature of some cells
- Battery-room temperature
- Electrolyte density of some cells

Annual measurement and recording:

- Voltage of all cells/bloc batteries
- Electrolyte temperature of all cells
- Electrolyte density of all cells

If the cell voltages deviate by more than + 0.1 V or -0.05 V from the average charge retention voltage (for blocs see table), call customer service.

	4V-bloc	6 V-bloc	10 V-bloc	12 V-bloc
+	0.14 V	0.17 V	0.22 V	0.24 V
-	0.07 V	0.09 V	0.11 V	0.12 V

Annual visual check:

- Screw connections
- Screw connections without locking devices have to be checked for tightness
- Battery installation and arrangement
- Ventilation

4. Tests

Tests have to be carried out according to IEC 60896-1. Special instructions like DIN VDE 0107 and DIN VDE 0108 have to be observed.

5. Faults

Call the services agents immediately if faults in the battery or charging unit are found. Recorded data as described in item 3. must be made available to the service agent. It is recommended that a service contract is taken out with your agent.

6. Storage and taking out of operation

To store or decommission cells/blocs for a longer period of time they should be fully charged and stored in a dry and cold but frost-free room, away from direct sunlight. To avoid damage the following charging methods can be chosen:

To prevent damage, choose the following charging methods:

1. Equalizing charges every three months as described under point 2.4.
Average ambient temperatures of more than 30° C may make more frequent equalizing charges necessary.
2. Float charging as under point 2.3.

7. Transport

To prevent any leakage of electrolyte, the cells/bloc batteries must be transported in an upright position. Cells/bloc batteries without any visible damage are not defined as hazardous goods under the regulations for transport of hazardous goods by road (ADR) or by railway (RID). They must be protected against short circuits, slipping, upsetting or damaging. Bloc batteries may be suitably stacked and secured on pallets (ADR and RID, special provision 598). It is prohibited to stack pallets. No dangerous traces of acid may be found on the exteriors of the packing units. Cells/bloc batteries whose cases leak or are damaged must be packed and transported as class 8 hazardous goods under UN no. 2794.

8. Technical data

The nominal voltage, the number of cells, the nominal capacity ($C_{10} = C_N$) and the battery type are described on the type plate. Other capacities (C_n) at different discharge currents (I_n) with the corresponding discharge times (t_n) see table 8.1.1 - 8.1.5.

8.1 Measurements, weights and capacities at different discharge times and final discharge voltage

8.1.1 Stationary lead acid bloc, cells and batteries type OPzS-LA acc. to DIN 40736 and DIN 40737 with positive tubular plates and negative grid plates, Nominal electrolyte density 1.24 kg/l

Discharge time [h]	Discharge data								Measurements and weights				
	Capacity [Ah]				discharge current [A]				Length max.	Width max.	Height ¹⁾ max.	Weight with acid approx. [kg]	Weight acid approx. [kg]
	10	5	3	1	10	5	3	1					
Final discharge voltage [Vpc]	1.80	1.77	1.75	1.67	1.80	1.77	1.75	1.67	[mm]	[mm]	[mm]	[kg]	[kg]
12V 1 OPzS 50 LA	50	43.0	37.5	26.5	5.0	8.6	12.5	26.5	275	208	385	35	15
12V 2 OPzS 100 LA	100	86.0	75.0	53.0	10.0	17.2	25.0	53.0	275	208	385	45	14
12V 3 OPzS 150 LA	150	129.0	112.5	79.5	15.0	25.8	37.5	79.5	383	208	385	64	19
6V 4 OPzS 200 LA	200	172.0	150.0	106.0	20.0	34.4	50.0	106.0	275	208	385	41	13
6V 5 OPzS 250 LA	250	215.0	187.5	132.5	25.0	43.0	62.5	132.5	383	208	385	56	20
6V 6 OPzS 300 LA	300	258.0	225.0	159.0	30.0	51.6	75.0	159.0	383	208	385	63	20

Discharge time [h]	Discharge data								Measurements and weights				
	Capacity [Ah]				discharge current [A]				Length max.	Width max.	Height ¹⁾ max.	Weight with acid approx. [kg]	Weight acid approx. [kg]
	10	5	3	1	10	5	3	1					
Final discharge voltage [Vpc]	1.80	1.77	1.75	1.67	1.80	1.77	1.75	1.67	[mm]	[mm]	[mm]	[kg]	[kg]
2 OPzS 100 LA	100	86	75.0	53.0	10	17.2	25.0	53.0	105	208	398	13.7	5.2
3 OPzS 150 LA	150	129	112.5	79.5	15	25.8	37.5	79.5	105	208	398	15.2	5.0
4 OPzS 200 LA	200	172	150.0	106.0	20	34.4	50.0	106.0	105	208	398	16.6	4.6
5 OPzS 250 LA	250	215	187.5	132.5	25	43.0	62.5	132.5	126	208	398	20.0	5.8
6 OPzS 300 LA	300	258	225.0	159.0	30	51.6	75.0	159.0	147	208	398	23.3	6.9
5 OPzS 350 LA	350	300	262.5	185	35	60.0	87.5	185.0	126	208	513	26.7	8.1
6 OPzS 420 LA	420	360	315.0	222	42	72.0	105.0	222.0	147	208	513	31.0	9.3
7 OPzS 490 LA	490	420	367.5	259	49	84.0	122.5	259.0	168	208	513	35.4	10.8
6 OPzS 600 LA	600	516	450	312	60	103.2	150	312	147	208	688	43.9	13.0
7 OPzS 700 LA	700	602	525	364	70	120.4	175	364	147	208	688	47.2	12.8
8 OPzS 800 LA	800	688	600	416	80	137.6	200	416	212	193	688	59.9	17.1
9 OPzS 900 LA	900	774	675	468	90	154.8	225	468	212	193	688	63.4	16.8
10 OPzS 1000 LA	1000	860	750	520	100	172.0	250	520	212	235	688	73.2	21.7
12 OPzS 1200 LA	1200	1032	900	624	120	206.4	300	624	212	277	688	86.4	26.1
12 OPzS 1500 LA	1500	1260	1116	744	150	252	372	744	212	277	838	108.0	33.7
14 OPzS 1750 LA	1750	1470	1302	868	175	294	434	868	212	277	838	114.0	32.7
16 OPzS 2000 LA	2000	1680	1488	992	200	336	496	992	215	400	815	151.0	50.0
18 OPzS 2250 LA	2250	1890	1674	1116	225	378	558	1116	215	400	815	158.0	48.0
20 OPzS 2500 LA	2500	2100	1860	1240	250	420	620	1240	215	490	815	184.0	60.0
22 OPzS 2750 LA	2750	2310	2046	1364	275	462	682	1364	215	490	815	191.0	58.0
24 OPzS 3000 LA	3000	2520	2232	1488	300	504	744	1488	215	580	815	217.0	71.0

¹⁾ The above mentioned height can differ depending on the used vents

8.1.2 Stationary lead acid cells type OCSM-LA

with positive tubular plates and negative copper stretch metal grid plates, Nominal electrolyte density 1.26 kg/l

Discharge time [h]	Discharge data								Measurements and weights				
	Capacity [Ah]				discharge current [A]				Length max.	Width max.	Height ¹⁾	Weight with acid approx.	Weight acid approx.
	10	5	3	1	10	5	3	1					
Final discharge voltage [Vpc]	1.80	1.77	1.75	1.67	1.80	1.77	1.75	1.67	[mm]	[mm]	[mm]	[kg]	[kg]
2 OCSM 160	160	140	120	84	16	28	40	84	124	206	522	12.5	8.3
3 OCSM 240	240	210	180	126	24	42	60	126	124	206	522	20.9	8.1
4 OCSM 320	320	280	240	168	32	56	80	168	124	206	522	23.9	7.9
5 OCSM 400	400	350	300	210	40	70	100	210	124	206	522	26.9	7.5
6 OCSM 480	480	420	360	252	48	84	120	252	145	206	522	31.5	8.1
7 OCSM 560	560	490	420	294	56	98	140	294	166	206	522	36.1	8.7
5 OCSM 575	575	500	427.5	300	57.5	100	142.5	300	145	206	698	41.6	11.5
6 OCSM 690	690	600	513.0	360	69.0	120	171.0	360	145	206	698	44.8	10.9
7 OCSM 805	805	700	598.5	420	80.5	140	199.5	420	210	191	698	58.1	16.6
8 OCSM 920	920	800	684.0	480	92.0	160	228.0	480	210	191	698	61.3	16.0
9 OCSM 1035	1035	900	769.5	540	103.5	180	256.5	540	210	233	698	71.4	19.7
10 OCSM 1150	1150	1000	855.0	600	115.0	200	285.0	600	210	233	698	74.6	19.1
11 OCSM 1265	1265	1100	940.5	660	126.5	220	313.5	660	210	275	698	84.8	22.8
12 OCSM 1380	1380	1200	1026.0	720	138.0	240	342.0	720	210	275	698	88.0	22.2
11 OCSM 1595	1595	1342	1188	792	159.5	268.4	396	792	210	275	848	108.7	28.7
12 OCSM 1740	1740	1464	1296	864	174.0	292.8	432	864	210	275	848	114.3	27.3
14 OCSM 2030	2030	1708	1512	1008	203.0	341.6	504	1008	214	399	824	140.5	40.8
16 OCSM 2320	2320	1952	1728	1152	232.0	390.6	576	1152	214	399	824	151.5	37.9
18 OCSM 2610	2610	2196	1944	1296	261.0	439.2	648	1296	214	489	824	182.0	52.0
20 OCSM 2900	2900	2440	2160	1440	290.0	488.0	720	1440	214	489	824	193.0	48.3
22 OCSM 3190	3190	2684	2376	1584	319.0	536.8	792	1584	214	579	824	223.5	61.6
24 OCSM 3480	3480	2928	2592	1728	348.0	585.6	864	1728	214	579	824	234.5	58.7

¹⁾ The above mentioned height can differ depending on the used vents

8.1.3 Stationary lead acid bloc batteries Energy Bloc

Nominal electrolyte density 1,24 kg/l

Antimony < 3% (see EN 50272-2)

Discharge time [h]	Discharge data								Abmessungen und Gewichte				
	Capacity [Ah]				discharge current [A]				Length max.	Width max.	Height ¹⁾	Weight including acid approx.	Weight of acid approx.
	10	5	3	1	10	5	3	1					
Final discharge voltage [Vpc]	1.80	1.80	1.80	1.75	1.80	1.80	1.80	1.75	[mm]	[mm]	[mm]	ca. [kg]	ca. [kg]
EB 1230	30.5	26.3	23.0	17.2	3.05	5.27	7.66	17.2	273	204	358	28.7	12.7
EB 1260	61.0	52.5	45.9	34.4	6.1	10.5	15.3	34.4	273	204	358	33.9	11.8
EB 1285	85.0	75.5	66.6	50.3	8.5	15.1	22.2	50.3	273	204	358	39.1	10.7
EB 12110	105	97.5	84.9	65.5	10.5	19.5	28.3	65.5	273	204	358	44.2	10.6
EB 12145	141	126	111	83.8	14.1	25.2	37.0	83.8	381	204	358	57.8	15.2
EB 12160	158	144	127	97.1	15.8	28.8	42.5	97.1	381	204	358	64.2	15.1
EB 6215	213	184	162	121	21.3	36.9	54.0	121	273	204	358	41.2	11.6
EB 6230	226	201	177	134	22.6	40.3	59.2	134	273	204	358	43.4	11.1
EB 6240	237	216	191	145	23.7	43.2	63.7	145	273	204	358	46.0	11.0
EB 6310	304	263	231	172	30.4	52.7	77.0	172	381	204	358	56.9	16.80
EB 6335	334	290	254	190	33.4	58.0	84.8	190	381	204	358	59.6	16.40
EB 6350	340	302	266	201	34.0	60.5	88.8	201	381	204	358	62.3	15.80

¹⁾ The above mentioned height can differ depending on the used vents

8.1.4 Stationary lead acid batteries type GroE acc. to DIN 40738

with positive Planté plates and negative grid plates, Nominal electrolyte density 1.22 kg/l

			Discharge data								Measurements and weights						
			Capacity [Ah]				discharge current [A]				Length max. [mm]	Width max. [mm]	Height ¹⁾ max. [mm]	Weight with acid approx. [kg]	Weight acid approx. [kg]		
Discharge time [h]	10	5	3	1	10	5	3	1	Final discharge voltage [Vpc]	1.80						1.79	1.78
3	GroE	75	75	69	64	50	7.5	13.8	21.3	49.8	182	153	411	17.5	6.6		
4	GroE	100	100	92	85	66	10.0	18.4	28.4	66.4	182	153	411	19.7	6.4		
5	GroE	125	125	115	107	83	12.5	23.0	35.5	83.0	182	153	411	21.9	6.2		
6	GroE	150	150	138	128	100	15.0	27.6	42.6	99.6	182	153	411	24.1	6.0		
7	GroE	175	175	161	149	116	17.5	32.2	49.7	116.2	182	153	411	26.3	5.8		
8	GroE	200	200	184	170	133	20.0	36.8	56.8	132.8	182	228	411	33.2	9.4		
9	GroE	225	225	207	192	149	22.5	41.4	63.9	149.4	182	228	411	35.4	9.2		
10	GroE	250	250	230	213	166	25.0	46.0	71.0	166.0	182	228	411	37.6	9.0		
11	GroE	275	275	253	234	183	27.5	50.6	78.1	182.6	182	228	411	39.8	8.8		
12	GroE	300	300	276	256	199	30.0	55.2	85.2	199.2	182	228	411	42.0	8.6		
13	GroE	325	325	299	277	216	32.5	59.8	92.3	215.8	182	338	411	52.5	14.1		
14	GroE	350	350	322	298	232	35.0	64.4	99.4	232.4	182	338	411	54.7	13.8		
15	GroE	375	375	345	320	249	37.5	69.0	106.5	249.0	182	338	411	56.9	13.6		
16	GroE	400	400	368	341	266	40.0	73.6	113.6	265.6	182	338	411	59.1	13.3		
17	GroE	425	425	391	362	282	42.5	78.2	120.7	282.2	182	338	411	61.3	13.0		
18	GroE	450	450	414	383	299	45.0	82.8	127.8	298.8	182	338	411	63.5	12.7		
5	GroE	500	500	458	415	310	50	92	138	310	328	268	590	95	34		
6	GroE	600	600	549	498	372	60	110	166	372	328	268	590	104	33		
7	GroE	700	700	641	581	434	70	128	194	434	328	268	590	113	32		
8	GroE	800	800	732	664	496	80	146	221	496	328	268	590	122	31		
9	GroE	900	900	824	747	558	90	165	249	558	328	268	590	131	30		
10	GroE	1000	1000	915	830	620	100	183	277	620	328	268	590	140	29		
11	GroE	1100	1100	1007	913	682	110	201	304	682	328	268	590	149	28		
12	GroE	1200	1200	1098	996	744	120	220	332	744	328	348	590	170	39		
13	GroE	1300	1300	1190	1079	806	130	238	360	806	328	348	590	179	38		
14	GroE	1400	1400	1281	1162	868	140	256	387	868	328	348	590	188	37		
15	GroE	1500	1500	1373	1245	930	150	275	415	930	328	348	590	197	36		
16	GroE	1600	1600	1464	1328	992	160	293	443	992	328	438	590	222	49		
17	GroE	1700	1700	1556	1411	1054	170	311	470	1054	328	438	590	231	48		
18	GroE	1800	1800	1647	1494	1116	180	329	498	1116	328	438	590	240	47		
19	GroE	1900	1900	1739	1577	1178	190	348	526	1178	328	438	590	249	46		
20	GroE	2000	2000	1830	1660	1240	200	366	553	1240	328	438	590	258	45		
21	GroE	2100	2100	1922	1743	1302	210	384	581	1302	328	528	590	285	58		
22	GroE	2200	2200	2013	1826	1364	220	403	609	1364	328	528	590	294	57		
23	GroE	2300	2300	2105	1909	1426	230	421	636	1426	328	528	590	303	56		
24	GroE	2400	2400	2196	1992	1488	240	439	664	1488	328	528	590	312	55		
25	GroE	2500	2500	2288	2075	1550	250	458	692	1550	328	573	590	325	60		
26	GroE	2600	2600	2379	2158	1612	260	476	719	1612	328	573	590	334	59		

¹⁾ The above mentioned height can differ depending on the used vents

8.1.5 Stationary lead acid batteries type OGi (LA)

with positive and negative grid plates, Nominal electrolyte density 1.26 kg/l,

* Nominal electrolyte density 1.24 kg/l

Bloc battery

					Discharge data								Measurements and weights				
					Capacity [Ah]				discharge current [A]				Length max. [mm]	Width max. [mm]	Height ¹⁾ [mm]	Weight with acid approx. [kg]	Weight acid approx. [kg]
Discharge time [h]		10	5	3	1	10	5	3	1	Final discharge voltage [Vpc]		1.80					
12V	1	OGi	28	LA	28	25.5	22.8	16.5	2.8	5.1	7.6	16.5	272	205	370	35.2	12.7
12V	2	OGi	55	LA	55	49.5	45.0	33.0	5.5	9.9	15.0	33.0	272	205	370	42.4	11.6
12V	3	OGi	83	LA	83	75.0	68.1	50.0	8.3	15.0	22.7	50.0	272	205	370	49.7	10.7
12V	4	OGi	110	LA	110	99.5	90.0	66.0	11.0	19.9	30.0	66.0	272	205	370	56.5	10.4
12V	5	OGi	137	LA	137	138.5	112.2	82.5	13.7	27.7	37.4	82.5	380	205	370	73.0	16.5
12V	6	OGi	165	LA	165	148.5	135.0	99.0	16.5	29.7	45.0	99.0	380	205	370	80.0	15.1
6V	7	OGi	192	LA	192	173.5	157.2	115.0	19.2	34.7	52.4	115.0	272	205	370	49.6	12.3
6V	8	OGi	220	LA	220	198.5	180.3	131.5	22.0	39.7	60.1	131.5	272	205	370	53.1	11.6
6V	9	OGi	247	LA	247	223.0	202.2	148.0	24.7	44.6	67.4	148.0	380	205	370	65.0	18.7
6V	10	OGi	275	LA	275	248.0	225.3	164.0	27.5	49.6	75.1	164.0	380	205	370	67.4	17.9
6V	11	OGi	302	LA	302	272.5	247.2	180.0	30.2	54.5	82.4	180.0	380	205	370	71.3	17.2
6V	12	OGi	330	LA	330	298.0	270.3	197.0	33.0	59.6	90.1	197.0	380	205	370	75.0	16.5

Single cell

2	OGi	50	LA*	50	45.0	36.6	26	5.0	9.0	12.2	26	69	160	351	6.3	2.3
3	OGi	75	LA*	75	67.5	54.6	39	7.5	13.5	18.2	39	69	160	351	7.0	2.1
4	OGi	100	LA*	100	90.0	71.4	51	10.0	18.0	23.8	51	125	160	384	11.5	4.9
6	OGi	150	LA*	150	135.0	107.4	75	15.0	27.0	35.8	75	125	160	384	13.3	4.6
8	OGi	200	LA*	200	177.5	143.1	98	20.0	35.5	47.7	98	155	160	384	16.8	5.8
10	OGi	250	LA*	250	222.5	178.8	120	25.0	44.5	59.6	120	194	160	384	20.9	7.3
4	OGi	260	LA	260	224.5	186.3	129	26.0	44.9	62.1	129	124	206	528	20.8	8.2
5	OGi	325	LA	325	280.0	233.1	161	32.5	56.0	77.7	161	124	206	528	22.9	7.9
6	OGi	370	LA	370	312.5	268.2	192	37.0	62.5	89.4	192	124	206	528	24.7	7.5
7	OGi	410	LA	410	347.5	303.0	224	41.0	69.5	101.0	224	124	206	528	26.6	7.3
8	OGi	440	LA	440	382.5	339.0	255	44.0	76.5	113.0	255	124	206	528	28.5	7.1
9	OGi	470	LA	470	417.5	375.0	287	47.0	83.5	125.0	287	124	206	528	30.6	6.9
10	OGi	530	LA	530	465.0	420.0	316	53.0	93.0	140.0	316	145	206	528	34.0	8.1
11	OGi	580	LA	580	515.0	465.0	346	58.0	103.0	155.0	346	166	206	528	38.3	9.8
12	OGi	620	LA	620	562.5	513.0	375	62.0	112.5	171.0	375	166	206	528	40.0	9.4
12	OGi	730	LA	730	585.0	579.0	383	73.0	117.0	193.0	383	254	210	528	50.3	17.5
14	OGi	800	LA	800	715.0	636.0	482	80.0	143.0	212.0	482	254	210	528	52.6	15.9
16	OGi	880	LA	880	770.0	687.0	520	88.0	154.0	229.0	520	254	210	528	56.6	15.5
19	OGi	1000	LA	1000	857.5	762.0	578	100.0	171.5	254.0	578	254	210	528	62.5	14.9
16	OGi	1260	LA	1260	1117.5	1002.0	718	126.0	223.5	334.0	718	233	210	699	78.2	18.3
18	OGi	1340	LA	1340	1187.5	1065.0	763	134.0	237.5	355.0	763	233	210	699	85.2	19.7
20	OGi	1520	LA	1520	1347.5	1209.0	869	152.0	269.5	403.0	869	275	210	699	95.2	22.3
22	OGi	1600	LA	1600	1420.0	1272.0	915	160.0	284.0	424.0	915	275	210	699	102.5	23.3

¹⁾ The above mentioned height can differ depending on the used vents

EXIDE Distributionscenter Berlin
ELEKTRO.TEC GmbH
 Eichborndamm 129-139
 D-13403 Berlin

Tel.: 030/4111024
 Fax: 030/4111025

www.elektrotec-berlin.de

info@elektrotec-berlin.de

EXIDE
 TECHNOLOGIES
 INDUSTRIAL ENERGY

State: March 2006